



# SZABO SCANDIC

Part of Europa Biosite

## Produktinformation



Forschungsprodukte & Biochemikalien



Zellkultur & Verbrauchsmaterial



Diagnostik & molekulare Diagnostik



Laborgeräte & Service

Weitere Information auf den folgenden Seiten!  
See the following pages for more information!



### Lieferung & Zahlungsart

siehe unsere [Liefer- und Versandbedingungen](#)

### Zuschläge

- Mindermengenzuschlag
- Trockeneiszuschlag
- Gefahrgutzuschlag
- Expressversand

### SZABO-SCANDIC HandelsgmbH

Quellenstraße 110, A-1100 Wien

T. +43(0)1 489 3961-0

F. +43(0)1 489 3961-7

[mail@szabo-scandic.com](mailto:mail@szabo-scandic.com)

[www.szabo-scandic.com](http://www.szabo-scandic.com)

[linkedin.com/company/szaboscandic](https://www.linkedin.com/company/szaboscandic) 

**Catalog Number:** 4637

**Product Description:** Corning® Spheroid Microplate, 1536-well, black clear round bottom, ultra-low attachment, with lid

**Component Materials:**

- Plate walls - Virgin Polystyrene, meets USP, Class VI requirements for plastic containers and closures. Black concentrate.
- Plate bottom - Polystyrene, meets USP, Class VI requirements for plastic containers and closures.
- Lid - Virgin Polystyrene, meets USP, Class VI requirements for plastic containers and closures.
- Surface - Proprietary hydrogel.

**Product Dimensions:**

Length of Plate	-	5.030 in.	Width of Square Well @ Top	-	.067 in.
Width of Plate	-	3.365 in.	Well bottom radius (Inside well)	-	.027 in.
Depth of Well	-	.244 in.	Well bottom radius (Outside well)	-	.031 in.
Tolerances of Dimensions	-	+/- .010 in.	Well bottom elevation	-	.071 in.
Working Volume per Well	-	12µL to 14µL	Height with Lid	-	.400 in.

**Sterility** - Product has been sterilized and dosimetrically released per the requirements of ANSI/AAMI/ISO 11137, "Sterilization of health care products- Radiation". Products meet a minimum Sterility Assurance Level (SAL) of 10<sup>-3</sup>.

**Animal Content:** Product does not contain materials of animal origin.

**Non-Pyrogenic:** Tested and met the criteria established in the current version of ANSI/AAMI ST 72, "Bacterial Endotoxins - Test methodologies, routine monitoring, and alternatives to batch testing" and USP <85>, "Bacterial Endotoxins Test". The acceptance level for product is ≤ 0.10 EU/ml or ≤ 4 EU/device.

**Optical Characteristics** - The product is made of opaque black polystyrene walls to minimize well to well crosstalk and background fluorescence. The bottom is made of clear thin polystyrene to permit direct microscopic viewing.

**Surface Characterization** - Surface is characterized to be hydrophilic and neutrally charged, composed of a covalently bound hydrogel layer that is biologically inert and non-degradable. This surface composition has been optimized for cell attachment and inhibition.

**Tissue Culture** - Tested for the ability to promote the growth and formation of 3D cellular spheroids of mammalian suspension cells in culture. Spheroid formation in ≥ 95% of the wells required for acceptance.

**Quality Control Testing** - Representative production samples are collected and inspected in accordance with current applicable product specifications. Inspection records are reviewed and approved by qualified personnel for product release. Key inspections and inline tests are listed below:

- Visual Inspection - Pass
- Packaging Inspection - Pass
- Well Bottom Elevation - Pass

**Lot Number Designation:**

8 Digit Lot Number: First 3 digits – Julian date, start of manufacturing; Next 2 digits – Year of manufacture; Last 3 digits – Batch identification.